

WAKOL D 3055 Universal Primer Parquet

Technical Information

Area of application

Ready-to-use dispersion-based primer for priming absorbant


- cement screed
- calcium sulphate screed
- gypsum fibre boards

before subsequent leveling parquet with Wakol parquet adhesives indoors.

Special properties



1)



2)

- solvent-free according to TRGS 610
- suitable for wheelchairs
- suitable for underfloor heating

1) Based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS: very low in emissions

2) Emission class according to French law

Technical data

Raw material base:	Polyurethane dispersion
Drying time:	on cement screeds following visible drying, approx. 30 minutes; on calcium sulphate screeds and gypsum fibre boards after approx. 2 hours
Cleaning agent:	water, before primer dries
Storage time:	12 months at room temperature
Storage temperature:	not under + 5°C, sensitive to frost
GISCODE:	D1
EMICODE nach GEV:	EC1 PLUS

Application and consumption³⁾:

WAKOL Primer roller, approx.
short-haired velour or 100 - 150 g/m²
foam roller

3) Consumption is dependent on surface structure and absorbability of subfloor

Subfloors

The subfloor and the climatic conditions of the room must meet the requirements of DIN 18356. Subfloors must be permanently dry, solid, and free from cracks, dirt and adhesion-inhibiting substances. Use a suitable mechanical procedure to remove separating layers.

Mechanically pretreat and thoroughly vacuum-clean calcium-sulphate-based screeds according to manufacturer's specifications or according to the currently applicable standards and codes.

Usage

Shake primer well before using. Apply WAKOL D 3055 Universal Primer Parquet with WAKOL Primer Roller, velour or foam roller on the subfloor, avoiding puddle formation. Wait until the primer has completely dried before continuing with bonding; pay careful attention to drying times.

Important

Do not use at temperatures below + 15°C. WAKOL D 3055 Universal Primer Parquet in cold weather, warm up in due time in heated room. All information is based on approx. 20°C and 65 % relative air humidity.

The shares of the used parquet adhesive should be observed.

Do not use WAKOL D 3055 Universal Primer Parquet under levelling compound. Excluded from this are partial fillings with WAKOL Z 640 Filling Compound, WAKOL Z 645 Filling Compound or WAKOL Z 505 Repair Compound, fine.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the currently applicable codes must be observed. We gladly provide technical advice.

The product data sheets can be found in their latest version at www.wakol.com.

This Technical Information of 08.12.2014 supersedes all previous versions.